



Hampford Research INC

Handcrafted Solutions For A High-Tech World

OPPI-PF6


FP 5384

General

OPPI-PF6 is a highly efficient UV curing agent used to initiate the photopolymerization of prepolymers in combination with mono or multifunctional monomers.

OPPI-PF6's unique composition provides excellent solubility, cure speed and high temperature stability, making it ideal for most epoxy based systems.

Chemical structure



Product information


PRODUCT TYPE:	Photo Acid Generator
PRODUCT NAME:	(4-octyloxyphenyl) phenyliodonium PF-6
CAS NUMBER:	125604-89-9
TRADE NAMES:	OPPI-PF6
APPLICATIONS:	Pressure Sensitive Adhesives, deep UV lithography,
KEY FEATURES:	Photo-acid generation for curing of epoxy and vinyl monomers. Also generates a free radical
PACKAGING:	sold as a solid or in reactive diluents
REGISTRATIONS:	TSCA (USA-CBI)
SHELF LIFE/STORAGE:	1 year when stored indoors at 25 (+/- 5) deg C

Hampford Research, Inc. disclaims any liability incurred in connection with the use of the data contained in this bulletin. Furthermore, nothing contained in this bulletin shall be construed as a recommendation to use any product in conflict with existing patents.

Typical properties

APPEARANCE: Off White Powder
MELTING POINT: 56-58 C

Absorption Spectrum



Packaging: 5kg, 18 kg fiber containers

Suggested starting formulation

OPPI-PF6 should be added between 1-3% for use with broad spectra mercury lamps. For LED applications, equal amounts of sensitizer (i.e. ITX or 9,10 DEA) should be used to help facilitate surface cure.

Safety and Handling

OPPI-PF6 should be handled in accordance with good industrial practice. Detailed information is provided in the SDS.

OPPI-PF6 is sensitive to visible light and any exposure to sunlight should be avoided.

Hampford Research, Inc. disclaims any liability incurred in connection with the use of the data contained in this bulletin. Furthermore, nothing contained in this bulletin shall be construed as a recommendation to use any product in conflict with existing patents.

Hampford Research, Inc. disclaims any liability incurred in connection with the use of the data contained in this bulletin. Furthermore, nothing contained in this bulletin shall be construed as a recommendation to use any product in conflict with existing patents.

Phone: (203) 375-1137

Hampford Research, Inc.
54 Veterans Boulevard
Stratford, CT 06615

Fax: (203) 386-9754